



Product Technical Bulletin

ORAJET® Series 3551 Inkjet Media Release 1, Effective May 2006

Description

ORAJET® Series 3551 is intended for medium-term to long-term use over flat surfaces, simple corrugations or rivets. This 2.75-mil, 7-year media features a smooth, ultra-glossy surface to produce vivid, life-like prints and a repositionable, solvent-based adhesive that can be removed with little or no adhesive residue for up to four years.

Product Data

Construction

This information is subject to change. Please ensure you are referencing the most recent Product Bulletin.

- **Face Film** – 2.75-mil smooth, ultra-glossy high performance vinyl film
- **Adhesive** – Grey, solvent-based, repositionable, permanent, pressure-sensitive adhesive with four-year removability with little or no adhesive residue
- **Liner** – 80-lb., PE-coated silicone paper

Physical Properties

The information stated below is based on testing results and intended solely as an information source. These values are given without guarantee and no warranty is implied or expressed. Oracal recommends the purchaser conduct independent tests prior to use in order to determine suitability for his/her intended application.

Outdoor Durability	7 years ¹
Application Surface Contours	Flat surfaces, simple corrugations, rivets
Minimum Surface/Air Application Temperature	+46° F
Temperature Resistance	Adhered to aluminum, -58° F to +194° F no variation
Resistance to Solvents and Chemicals	At room temperature, 72h after adhesion to aluminum, short-term resistant to most oils and greases, fuels, aliphatic solvents, weak acids, salts and alkalis
Shelf Life	2 years (68°F/50% relative humidity)
Adhesive Power	(FINAT-TM 1, after 24h average) min. 4.1 lb/in ²
Tensile Strength (along)	(DIN EN ISO 527) min.19 MPa
Tensile Strength (across)	(DIN EN ISO 527) min.19 MPa

Elongation at Break (along)	(DIN EN ISO 527) min. 130%
Elongation at Break (across)	(DIN EN ISO 527) min. 150%
Dimensional Stability	(FINAT-TM 14) adhered to steel, no shrinkage in cross direction, in length <.008"

¹ Applies to graphics created using unprinted, unlaminated film with no UV inhibitors and installed with vertical exposure within 10°. In certain climates, some color fade will occur.

Compatible Substrates

- Acrylic
- Aluminum
- Glass (uncoated)
- Painted metal
- Polycarbonate²
- Rigid vinyl
- PETG
- Smooth, non-porous, painted surfaces

² Refer to manufacturer's suggestions on the processing and handling of this material. Ensure that the graphics are applied to the proper side of the material.

Compatible Products

ORAJET® Series 3551 Inkjet Media is compatible with most of today's popular solvent, eco-solvent and UV curable printers.

Printing and Fabrication

Color Profiles

Oracal USA has developed a proprietary Advanced Color Management program to provide exceptional technical support for all of our ORAJET® inkjet media, including Series 3551. For optimal printing results, it is imperative that your printer is calibrated using RIP software and the appropriate color profile. Color profiles can be downloaded from www.oracal.com. For additional color management support, please call Oracal USA's Technical Support team at 1-800-ORACAL-1 (672-2251).

Ink Drying

Allow printed film to dry flat for at least 24 hours at at least 70°F before applying a laminate or cutting, trimming, mounting or applying the graphic.

Laminating

To provide UV protection and extend the life of the ink for up to four years, Oracal recommends laminating all digital prints. Series 3551 is compatible with ORAGUARD® Series 215 (flat surfaces only) or Series 290 laminates.

Application Methods

ORAJET® Series 3551 is suitable for dry or wet (flat surfaces only) application. For best results, all digital prints must be laminated, in which case application tape is not required. If you choose not to laminate, use a low-tack application tape to protect the print during application. **NOTE: Vehicle wrap graphics MUST be laminated.**

Preparing the Surface

When using materials that tend to outgas, such as polycarbonate or polystyrene products, we recommend the following steps:

1. Clean the surface, mount a piece of film to it, and store at 140° F for 24 hours.
2. If bubbles form after 24 hours, outgassing is still occurring. Either treat the plastic with a heat source or store it for an extended period at room temperature conditions in order to cure the substrate prior to application of the vinyl.

The high-quality special adhesives used on Oracal pressure-sensitive films create an excellent bond with most clean, smooth, weather-resistant surfaces that are free of grease, dust or any contaminants. For a long-lasting bond, the target surfaces must be properly prepared. **Be sure to check the directions provided by the manufacturer of the substrate you are using to determine the recommended cleaning method for that surface.** Gas bubbles may form between the film and the surface if any solvent residue remains as a result of improper cleaning or if paint on the surface is too fresh. Freshly lacquered or painted surfaces should be allowed to stand for at least three weeks after complete curing before adhering the film. *The compatibility of selected lacquers and paints should be tested by the end-user prior to use.*

Application Temperatures

Oracal films should never be adhered at temperatures below 46° F. Newly fabricated sign faces should remain in the application environment for at least 24 hours to promote uniform adhesion characteristics and allow any residual moisture to evaporate. A significant drop in temperature should be avoided during the first 24 hours after adhesion.

Removing the Release Liner

Lay the cut film on a flat surface with the film side down. Pull back only as much release liner as required to begin mounting. Always draw the release liner from the film, never the other way around.

Dry Application

1. Arrange the film on the surface to which it is to be adhered and pull down approximately six to eight inches of release liner. Be sure to keep the liner intact, but draped behind the graphic to keep adhesive off of the substrate until the instance of application (Diagram 1).
2. Apply the film in firm, overlapping strokes; be sure to establish a smooth baseline across the entire graphic.




Diagram 1

3. Continue with overlapping strokes until the entire graphic has been applied.
4. When using ORATAPE masking tape, pull slowly away from the film at a 180° angle. If needed, the top of the masking tape can be lightly sprayed with water to allow for easier release from the graphic.

Wet Application

Recommended for flat surfaces only. Wet adhesion should only be done in ambient temperature environments of at least 70° F.

1. Prepare Application Fluid – For best results, use a prepared application fluid that is designed for use with vinyl sign materials.
2. Clean and Prepare the Substrate – Clean flexible face materials using the prepared application fluid described in Step 1. **Never use alcohol to clean acrylic or polycarbonate.**
3. Film Application for Full-Coverage Sign Faces
 - a. Lay the substrate face up on a clean surface.
 - b. Spray the substrate with prepared application fluid.
 - c. Wipe off the film with a clean, lint-free cloth.
 - d. Lay the film, liner side up, in a dry location near the wetted surface.
 - e. Spray the exposed adhesive side with application fluid and place it on the substrate.
 - f. Position the cut film where you want it. The wet application method allows for more precise positioning of film.
 - g. Squeegee the film to the surface using sweeping, overlapping motions. Be certain that there is no water left between the substrate and adhesive to avoid bubbles and ensure a positive bond.

For wet adhesion, we recommend using a low-tack application tape if the graphic is not laminated. After a short drying period, remove the application tape carefully at a 180° angle.

Application Tips

- Seams can be made using the overlap method. It is recommended that overlaps and seams measure no more than 1/8".
- Puncture air bubbles with an air release tool. Do not use a knife or razor.
- If using application tape, always remove it at a 180° angle and immediately re-squeegee the film.
- Apply heat to all seams, then re-squeegee.
- Rivets should be treated as a flat panel during installation. Puncture with an air-release tool, apply heat and finish with a rivet brush.
- Cutbacks should be performed soon after application as adhesion builds with time.

Oralife Component System Warranty

The Oralife Component System (OCS) warranty from Oracal USA includes specially matched media and laminates to fit almost any graphic application where a pressure-sensitive adhesive is needed. Combined with your approved wide-format inkjet printer and corresponding OEM ink sets, the OCS warranty can help you achieve an unrivaled level of performance and guaranteed reliability for your outdoor digital prints. For more information, visit www.oracal.com or contact us at 1-800-ORACAL-1 (672-2251).

General Warranty

Oracal USA warrants its pressure-sensitive vinyl films to be free of defects in materials and manufacture, and to perform as stated in published product technical information bulletins if properly stored and applied. Oracal USA will, at its discretion, either replace defective material or refund the purchase price of any ORACAL®, ORAJET®, ORAGUARD®, ORALITE® or ORAMASK® materials that do not meet this warranty within the specified effective performance life. The customer assumes responsibility in determining product suitability for intended use. Oracal USA shall not be liable for any direct, indirect or consequential damages arising from the use or inability to use the product. This warranty is declared in lieu of any other claim, whether expressed or implied, and is not subject to interpretation.

If you are in extreme climate zones (Southwestern United States, desert, tropics, etc.), South America, Latin America or the Caribbean, contact Oracal USA for specific warranty information for your area.

Shipping, Storage, Shelf Life

- Film must be stored at 68° F/50% relative humidity.
- For optimal product quality and performance, film must be stored in a dry, clean area, out of direct sunlight.
- Shelf life of Oracal® Series 8500F must not exceed two years from the date it is received from Oracal USA

Contact Us

Oracal USA
A Division of LIG International, Inc.
7251 Salisbury Road
Jacksonville, FL 32256
Telephone: 904-726-9597
Toll Free: 888-672-2251
Fax – 904-265-3355
www.oracal.com